

Moriaci kúpeľ

Stainless Steel Pickling Baths

Opis produktu

Ponorné mořidlo odstraňuje nábehové farby, valcované okuje, okuje zo zvárania, korózne produkty (tenká vrstva hrdze) a feritické výlisky všetkých moriteľných nerezových materiálov. Produkty T100 neobsahujú kyselinu chlorovodíkovú.

Výber produktu

T 100 hotová zmes
T 100 koncentrát (1: 1 riediteľný s vodou)
N 100 údržbový koncentrát (vyrobený na základe analýzy moriaceho kúpeľa na zákazku)

Použitie

Optimálny čas použitia moriaceho kúpeľa závisí od teploty, materiálu a stavu povrchu a musí byť odskúšaný. Približné hodnoty:
1.4301 30 minút
1.4571 cca 60-180 min.
Vysoko legované ušľachtilé ocele a špeciálne materiály vyžadujú dlhší čas morenia!

Servis

Optimálna kvalita povrchu a časy morenia vyžadujú inteligentné riadenie kúpeľa. Pre tento účel je nutná znalosť obsahu kyselín a akumulácie kovov (obsah železa) v moriacom kúpeľi. Náš servis je vytvorený na základe požiadaviek analýz, riadi výrobu potrebných N100 koncentrátov a informuje o opatreniach potrebných na údržbu kúpeľa.

Product Description

The Pickling bath removes annealing colours, welding scale and corrosion products on weld seams and surfaces of stainless steel. T100 does not contain hydrochloric acid and conforms with the KWU regulations equipment in nuclear power facilities.

Product Selection

*T 100 Ready mixed
T 100 Concentrate (1:1 dilute with water)
N 100 Maintenance Concentrate (Additions subject to Analysis)*

Application

*The optimum application time in the pickling bath depends on temperature, material and surface conditions and has to be checked by trial. Approx. Values:
1.4301 approx. 30 mins.
1.4571 approx. 60 - 180 mins.
Higher alloyed stainless steel and special alloy steels may need longer pickling times.*


Service

Our service programme includes the control of the pickling bath for acid and metal content, as well as the calculation of the required addition of the N100 maintenance concentrate on customers demand.

Nepoužívať a neskladovať výrobok na priamom slnečnom svetle alebo v blízkosti iných extrémnych zdrojov tepla. Dodržujte R- a S-vety na základe dodaných etikiet na obale.

Do not use and store product under heat influence.

Please observe the hazard and safety advise on container label.



Všetky údaje sú nezáväznú. Pred použitím si prosím vyskúšajte produkt. Vyhradujeme si právo na zmeny.

The indication of product suitability and associated notes are based on our experience, are not recommendations and are not legally binding. Please test product before use. We reserve the right to amendments.